



 3093 100
 3094 100






 3093 101
 3094 101





 3093 102
 3094 102





 3093 103
 3094 103






 3093 104
 3094 104




 3093 105
 3094 105




 3093 106
 3094 106





 3093 107
 3094 107



 3093 108
 3094 108



 3093 109
 3094 109



- > 10 colours available both in sheets 23 m x 2 m and tiles 61 x 61 cm
- > 2 mm thickness
- > Colour coordinated with iQ Granit
- > $5 \times 10^4 \leq R \leq 10^6$ ohms
- > Unique conductive iQ PUR
- > iQ Unique Surface Restoration
- > Market's best Life Cycle Cost

PVC Heavy Traffic – Special Applications

Electrostatic Floors



- > A new generation of static control floorings
- > iQ Granit SD for static dissipation
- > iQ Toro SC or static conductivity
- > Unique conductive iQ PUR
- > iQ Unique Surface Restoration
- > Market's best life cycle cost

Technical data	iQ Toro SC	iQ Granit SD	
Classification	EN 685 commercial industrial UPEC Classification NF UPEC certificate number (Ref NF189)	Classes: 34 43 U4 P3 E2/3 C2 312-016.1	Classes: 34 43 U4 P3 E2/3 C2 312-014.1
Type of flooring	EN 649	Permanently static conductive pressed homogeneous vinyl flooring	Permanently static dissipative pressed homogeneous vinyl flooring
Wear layer thickness	EN 429	2.00 mm	2.00 mm
Total thickness	EN 428	2.00 mm	2.00 mm
Total weight	EN 430	3 000 g/m ²	3 000 g/m ²
Polyurethane reinforcement (iQ PUR)		Yes	Yes
Abrasion group			
Thickness loss	EN 660: Part 1	Group P: ≤ 0.15 mm	Group P: ≤ 0.15 mm
Volume loss	EN 660: Part 2	Group P: ≤ 4.0 mm ³	Group P: ≤ 4.0 mm ³
Residual indentation	EN 433	Approx. 0.03 mm	Approx. 0.03 mm
Castor chair test	EN 425	Suitable	Suitable
Dimensional stability	EN 434	≤ 0.40 % for rolls ≤ 0.25 % for tiles	≤ 0.40 % for rolls ≤ 0.25 % for tiles
Reaction to fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	B _s s1 ≥ 8 kW/m ² Pass	B _s s1 ≥ 8 kW/m ² Pass
Electrical insulation	VDE 100, Part 600	R _i ≤ 5 x 10 ⁹ ohms	R _i ≤ 5 x 10 ⁹ ohms
Static electrical charge	EN 1815	< 2 kV	< 2 kV
Electrical resistance	ESD-approval SP-method 2472 EN 1081 EN/IEC 61340-4-1 EN/IEC 61340-4-5	R ≤ 10 ⁹ ohms R: 5x10 ⁸ ≤ R ≤ 10 ⁹ ohms R: 5x10 ⁸ ≤ R ≤ 10 ⁹ ohms 5x10 ⁸ ≤ R ≤ 10 ⁹ ohms ≤ 3.5x10 ⁹ ohms	10 ⁹ ≤ R ≤ 10 ⁹ ohms R: ≤ 10 ⁹ ohms R: ≤ 10 ⁹ ohms R: ≤ 10 ⁹ ohms
Impact sound resistance	EN ISO 717/2	Approx. + 4 dB	Approx. + 4 dB
Light fastness	EN ISO 105-B02	≥ level 6	≥ level 6
Chemical resistance	EN 423	Good resistance	Good resistance
Fungi and bacteria resistance	DIN EN 846-A/C	Does not favour growth	Does not favour growth
Slip resistance	DIN 51130 EN 13893	R9 ≥ 0.3	R9 ≥ 0.3
Thermal resistance	DIN 52612/EN 12667	Approx. 0.01 m ² K/W	Pending
Underfloor heating		Suitable - max 27 °C	Suitable - max 27 °C
Colours		10	9
Form of delivery	EN 426 EN 427	Rolls: 23 rm x 2 m Tiles: 61 x 61 cm	Rolls: 23 rm x 2 m Tiles: 61 x 61 cm

The above information is subject to modifications for the benefit of further improvement (09/08).

For more detailed technical information, please contact Tarkett.
Follow Tarkett's installation and maintenance instructions carefully.
Please refer to page 230.



iQ Toro SC
iQ Granit SD

pages 190-191
pages 192-193